SILFIT Z 91

Field of application: Elastomers

1. Description

SILFIT Z 91 is a natural combination of corpuscular silica and lamellar kaolinite, which has been subjected to a heat treatment.

The components and the thermal process lead to a product that offers special performance benefits as a functional filler.

Characteristics

Appearance		free-flowing powder
Color CIELAB scale:	L* a* b*	96.5 - 0.2 1.0
Residue > 40 µm		10 mg/kg
Volatile matter at 105 °C		0.2 %
Densitiy		2.6 g/cm³
Particle size distribution	D_{50} D_{97}	2.1 µm 9.5 µm
Surface area BET		10 m²/g
Oil absorption		65 g/100 g
pH value		6.5
Equilibrium moisture content at 23 °C: 50 % relatice humidity 80 % relative humidity 90 % relative humidity		 0.12 % 0.22 % 0.54 %

Packaging

Paper bags	á 25 kg
EVA bags	≤ 20 kg
Big Bags	600 - 900 kg
Bulk	on demand

Shelf life

Unlimited if stored properly under dry conditions.

2. Applications

In elastomer applications SILFIT Z 91 can be used as a functional filler either on its own or in combination with other non-reinforcing or reinforcing fillers.

Information on compliance with certain regulations/recommendations and other safety-related aspects: Product safety information

Fields of application

In general SILFIT Z 91 is suitable for any rubber products used for technical applications.

Its particular properties are that it provides a balanced relationship between tensile strength, tear strength, low compression set and excellent extrusion properties.

It is particularly suitable for very bright or white compounds.

SILFIT Z 91 also provides advantages in the following instances:

- very high dispersion requirements:
- compounds with a high oil content
- automotive profiles with very low surface defect rates
- products with extremely thin walls (membranes)
- very high surface quality requirements (roller coverings and offset blankets)
- prevention of filler caused mold fouling during the injection process or deposits in the orifice die (Plating) during extrusion
- very low chloride content (washing machine gaskets)

Methods of processing:
Any process commonly used in the rubber industry.

Elastomers:
BIIR, BR, CIIR, CR, HNBR, IIR, IR, NBR, NR, PNR, SBR;
CM, CSM, EPM, EPDM, EVM, Q

Dosage:
Generally in the range from 50 to 300 phr, depending on application, formulation and requirements.

3. Benefits

- low sieve residues
- good and rapid incorporation
- very good dispersion, also in critical compounds
- good flow properties
- excellent surfaces
- excellent extrusion properties
- no negative influence on curing rate
- low tensile and compression set
- high electrical resistance
- good aging properties
- high chemical resistance
- complies with the standards on articles in contact with foodstuffs of the BfR and FDA
- matting effect

SILFIT Z 91 also provides the following benefits compared with Sillitin:

- lower moisture content, less moisture absorption
- lower chloride content
- very high brightness
- very high color-neutrality
- improved dispersion behavior like the Sillitin puriss grades
- slightly improved extrusion properties
- markedly improved compression set possible
- best combination of extrusion properties and compression set (within the range of non surface treated grades)
- outstandingly low dielectric losses in high voltage cable insulations

4. Comparison of properties

		SILLITIN V 85	SILLITIN V 88	SILLITIN N 82	SILLITIN N 85	SILLITIN N 87	SILLITIN Z 86	SILLITIN Z 89	SILFIT Z 91	SILLITIN P 87
Color neutrality		●●	●●●●●	●	●●	●●●	●●	●●●●	●●●●●●	●●
Extrusion	Profile quality	●	●	●●●	●●	●●	●●●	●●●	●●●○	●●●●
	Collapse resistance	●	●	●●●	●●	●●	●●●	●●●	●●●	●●●●
	Matting effect	●●●●	●●●●	●●●	●●●	●●●	●●	●●	●●	●
Viscosity		●	●	●●●	●●	●●	●●●	●●●	●●○	●●●●
Tensile strength		●	●	●●●	●●	●●	●●●	●●●	●●●	●●●●
Tear resistance		●	●	●●●	●●	●●	●●●	●●●	●●●	●●●●
Compression set		●	●	●●●	●●	●●	●●●	●●●	●○	●●●●
Rebound elasticity		●●●●	●●●●	●●●	●●●	●●●	●●	●●	●●	●
Abrasion loss		●●●●	●●●●	●●	●●●	●●●	●●	●●	●●	●

● = low ●●●●●● = high

5. Application examples

Plating

Prevention of filler caused mold fouling during the injection process or deposits in the orifice die (plating) during extrusion
Technical report: “Die plating”

Car body seals

- excellent extrusion properties
- quick cure
- higher tensile strength, higher tear resistance and markedly better compression set compared with calcined clay in non-conductive compounds
- generally low compression set, also testing according to Volkswagen VW PV 3307
- prevention of filler caused deposits in the orifice die (plating) during extrusion

Technical report: “Silfit Z 91 in Car Body Seals”

Wasching machine gaskets

- higher tensile strength and higher tear resistance versus calcined clay
- replacement of precipitated silica without deteriorating properties, faster cure and lower swelling in water and detergent lyes
- prevention of filler caused mold fouling
- very low chloride content

Technical report: “Silfit in Grey Colored Washing Machine Gaskets”

White building profiles (window and facade seals)

- good extrusion properties
- slightly higher tensile strength
- lower compression set and more neutral white color (less yellow tint) versus calcined clay

Technical report: “Calcined Neuburg Siliceous Earth in White Building Profiles”

Medium to high voltage cable insulation

- better dielectric loss factor tan δ
- lower sieve residue
- higher tensile strength versus calcined clay

Technical report: “Calcined Neuburg Siliceous Earth in Medium and High Voltage Cable Insulation

All technical reports are available at our homepage www.hoffmann-mineral.com.

Our applications engineering advice and the information contained in this memorandum are based on experience and are made to the best of our knowledge and belief, they must be regarded however as non-binding advice without guarantee. Working and employment conditions over which we have no control exclude any damage claim arising from the use of our data and recommendations. Furthermore we cannot assume any responsibility for patent infringements, which might result from the use of our information.

Münchener Straße 75 • DE-86633 Neuburg (Donau)
Phone +49 8431 53-0 • info@hoffmann-mineral.com